

## Q7200 LEF EXPANDED POLYSTYRENE PRODUCT DATA SHEET VOC COMPLIANT - ALL STATES

**Q7200 HIGH SOLIDS, HIGH TEMPERATURE SPRAY ADHESIVE** is a fast tack, high shear strength adhesive. Q7200 is especially formulated for bonding expanded polystyrene (EPS) to itself and other porous, non-porous, rigid and non-rigid substrates. When applied according to directions it will not cavitate or pit EPS. Q7200 can be used for permanent or temporary bonding of expanded polystyrene to polystyrene or other substrates such as wood, particle board, plywood, etc. It is also great for holding tanks in boats and RV's, poly foam, fiberglass insulation and EPS filler for bath tubs, bonding tub surrounds to walls, exhibit displays and scenery, model building and sculptures, hot and cold insulated panel systems, and many other applications. Product should be used at room temperature or at least at 70°F.

Container Size	20 Fluid oz. Container	11# DOT 923-267 424.7 CU. In.	38# DOT 923-933-39 & TC -39M	177# TC #14761	355# TC 200 Gallon
<b>Product Description</b>	<b>Aerosol Adhesive</b>	<b>Canister Adhesive</b>	<b>Canister Adhesive</b>	<b>Cylinder Adhesive</b>	<b>Cylinder Adhesive</b>
<b>Net Weight</b>	14 Ounces	9 lbs.	30 lbs.	130 lbs.	270 lbs.
<b>Weight Per Gallon</b>	6.2	6.2	6.2	6.2	6.2
<b>Can Per Case</b>	12	1	1	1	1
<b>Case Dimensions - Inches</b>	10.875"L X 8.125" W X 9.375" H	10.00"L X 10.00" W X 17.25" H	12.50"L X 12.50" W X 18.00"H	16" in diameter X 49" High	25" in diameter X 42" High
<b>Case Weight</b>	14.7 Pounds	17.0 Pounds	44.0 Pounds	199.0 Pounds	417.00 Pounds
<b>Cases Per Pallet</b>	08	60	36	9	4
<b>Appearance</b>	Natural/Blue	Natural/Blue	Natural/Blue	Natural/Blue	Natural/Blue
<b>Odor</b>	Slight Solvent	Slight Solvent	Slight Solvent	Slight Solvent	Slight Solvent
<b>Solvent System</b>	Hexane, Cyclohexane	Hexane, Cyclohexane	Hexane, Cyclohexane	Hexane, Cyclohexane	Hexane, Cyclohexane
<b>Propellant</b>	Dimethyl Ether	Dimethyl Ether	Dimethyl Ether	Dimethyl Ether	Dimethyl Ether
<b>Open Time</b>	20-30 Minutes	20-30 Minutes	20-30 Minutes	20-30 Minutes	20-30 Minutes
<b>Tack Time</b>	3-4 Minutes	3-4 Minutes	3-4 Minutes	3-4 Minutes	3-4 Minutes
<b>Heat Resistance</b>	Max Temp 160°F	Max Temp 160°F	Max Temp 160°F	Max Temp 160°F	Max Temp 160°F
<b>Viscosity</b>	5,000 cps #1 SPINDLE @10 RPM	5,000 cps #1 SPINDLE @10 RPM	5,000 cps #1 SPINDLE @10 RPM	5,000 cps #1 SPINDLE @10 RPM	5,000 cps #1 SPINDLE @10 RPM
<b>Solids</b>	32% +/- 2%	32% +/- 2%	32% +/- 2%	32% +/- 2%	32% +/- 2%
<b>Spray Pattern</b>	Web	Web	Web	Web	Web
<b>VOC %</b>	65%	245.38g/l	245.38 g/l	245.38 g/l	245.38 g/l
<b>VOC Compliant for CA &amp; OTC</b>	Yes	Yes	Yes	Yes	Yes
<b>Aerosol Flammability Level</b>	Level 3, Flammable	Level 3, Flammable	Level 3, Flammable	Level 3, Flammable	Level 3, Flammable
<b>Warranty Period</b>	One Year From Date of Shipment	One Year From Date of Shipment	One Year From Date of Shipment	One Year From Date of Shipment	One Year From Date of Shipment
<b>DOT Proper Shipping Name</b>	Consumer Commodity ORM-D for domestic ground shipment. (See MSDS for additional shipping info)	UN3161/Class 2.1 for domestic ground shipment. (See MSDS for additional shipping info)	UN3161/Class 2.1 for domestic ground shipment. (See MSDS for additional shipping info)	UN3161/Class 2.1 for domestic ground shipment. (See MSDS for additional shipping info)	UN3161/Class 2.1 for domestic ground shipment. (See MSDS for additional shipping info)

Office: 678.494.1112 • Fax: 678.494.1113 • 313 Bell Park Drive • Woodstock, GA 30188

**Where Quality and Service are Number 1**

[www.losorea.com](http://www.losorea.com) • [www.qualityaerosols.com](http://www.qualityaerosols.com)